



SportWalk®

Issue Date: 12/1/2020 Version 1.4

DESCRIPTION

SportWalk® is a white textured, printable non-slip media engineered with an aggressive adhesive system which adheres to a wide variety of smooth surfaces and is safe for pedestrian traffic. This product is UL410 certified for slip resistance.

APPLICATION

SportWalk® is a one-step solution for indoor and short-term outdoor event graphics. It is ideal for marathons, parades, retail point-of-purchase, trade shows, sporting and other outdoor events.

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC - 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.021 inch (0.580 mm) 0.002 inch (0.051 mm) 0.007 inch (0.178 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	55 oz/in (66 N/100 mm) 75 oz/in (82 N/100 mm)
- Powder coated surfaces *	15 minute dwell 24 hour dwell	40 oz/in (44 N/100 mm) 55 oz/in (60 N/100 mm)
- Polyethylene	15 minute dwell 24 hour dwell	20 oz/in (22 N/100 mm) 25 oz/in (27 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2" x 1/2" x 1000g	<5 hours
Tack	PSTC - 6 Rolling Ball Tack	< 5 inches

** Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance and should be evaluated for the compatibility of the product to the specific surface.*



PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Coefficient of Friction (Static)	ASTM D-2047	0.65
Service Temperature High	14 days at 220°F	No visible effects, moderate shrinkage & high elasticity
Low	14 days at -20°F	No visible effects
CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed and product is immediately tested for scrape resistances, delaminating, and other visual effects.)	Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Recommended Not Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended Not Recommended Recommended Recommended

Note: While the data contained herein is believed to be reliable averages of the product’s properties, the data should not be used for specification purposes. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.