

UltraCarpet® Extra is a white, tufted-pile carpet made specially for solvent, eco-solvent, UV, Latex and screen printing. The ink will not scratch off and drying time is minimal. UltraCarpet Extra has been engineered for indoor, digitally printed carpet or doormats. The material may be used outdoors for short periods of time. UltraCarpet Extra is ideal for corporate lobbies, waiting areas, foyers, tradeshow booths and floor graphics. Available in widths from 71" - 196".

Material Details

| CHARACTERISTICS | TEST METHOD | METRIC | ENGLISH |
|-------------------|----------------------|---------------------------------|---------------------------------|
| Pile | N/A | 100% polyamide | 100% polyamide |
| Construction | N/A | 1/10" Top Tuft | 1/10" Top Tuft |
| Total Height | N/A | 5 mm | 0.2" |
| Tuft Density | N/A | 165900 /m ² | 15412.5/sq.ft |
| Pile Weight | DIN EN ISO 2286-2 | 300 g/m ² | 8.8 oz/yd ² |
| Total Weight | DIN EN ISO 2286-21 | 0.900 kg/m ² – 1.100 | 0.900 kg/m ² – 1.100 |
| Primary Backing | ISO 13937-2-2002 | AB and Latex | AB and Latex |
| Pile Height | DIN 53351 | 3 mm | 0.12" |
| Fastness to Light | ISO 105 B01 (1 tm 8) | < 5 | < 5 |
| Fire Resistance | DIN 4102 | Norm Bfl / s1 | Norm Bfl / s1 |

Applications

| | Back-lit | Banner | Billboard | Blockout | Building Wrap | Carpet | Floor Mats | Truckside |
|--------------|----------|--------|-----------|----------|---------------|--------|------------|-----------|
| Applications | | | | | | ■ | ■ | |

Ink Printability

| Solvent | Eco Solvent | UV | Latex | Screen Printing | Dye Transfer | Dye Direct |
|---------|-------------|----|-------|-----------------|--------------|------------|
| ■ | ■ | ■ | ■ | ■ | | |

Available Sizes

| Metric (m) | English (inches) |
|------------------|------------------|
| 1.80, 3.20, 5.00 | 71, 126, 196 |

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guarantee and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of the material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)